

Product Data Sheet

Cromadex Liquid Coatings

Cromadex 440 Topcoat One Pack Polyurethane Fine Texture Topcoat

| Product Description | Cromadex 440 is a one pack topcoat that comes in a fine texture finish that adds value to your product. The product uses polyurethane technology providing excellent colour retention. | | | | | |
|--|--|--|----------------------|--|----------|--|
| | The product has a long wet edge making it easier to apply to large items with no dry spray. Cromadex 440 is available in the full Cromadex range of colours, including BS, RAL and special matches all in a lead free finish. Life expectancy of up to 7 years in a C3* environment when used with a suitable Cromadex primer. See Extra Life brochure for full details. | | | | | |
| | | | | | | |
| Extra Life | | | | | | |
| | * as determined in ISO12944: 2018 | | | | | |
| Products and Ancillaries | 440 Topcoat 05-46 Thinner (Standard) 05-44 Thinner (Slow) | | | | | |
| Suitable Substrates and Preparation | Mild Steel | Degrease with Cromadex 678 Spirit Wipe and abrade steel with P180. If necessary blast clean to remove millscale, minimum surface preparation SA2. Apply suitable Cromadex primer | | | | |
| | Aluminium & Galvanised Steel | Apply Cromadex 903 Chromate-Free Etch Primer (then other Cromadex primer is required to increase film build) | | | | |
| | Stainless Steel | Use of Cromadex 903, AQ58, 750 or 850 primer is required | | | | |
| Application Details | Thinning Ratio | 5 parts 440 Topcoat 1 part Thinner (dependent on application equipment) | | | | |
| | Spraying Viscosity | 45 – 65 seconds ISO Cup4 @ 20°C 25 – 30 seconds BS 4 Cup @ 20°C | | | | |
| | Approved Thickness | 25 – 35 micro | ons DFT | 50 – 70 microns V | NFT | |
| | Spray Gun Conventional Suction Feed HVLP Pressure Feed HVLP | Fluid tip siz 1.4 – 1.8 mm 1.4 – 1.8 mm 1.0 – 1.4 mm | ו ו | Working pressur 3.5 – 4.2 bar 0.7 bar (max) 0.7 bar (max) | e | |
| | | Other methods not suitable | | | | |
| Drying and Overcoating | Substrate Temperature | Drying Times Overcoating Times Touch Dry Through Dry Minimum Maximu | | ting Times Maximum | | |
| | 20°C 35°C | 3 hours 2 hours | 12 hours 10 hours | Not reco | ommended | |
| | Force Drying | Flash-off for 10-15 mins, then 60-80°C for 30 mins | | | | |
| | Full Properties | 7 days | | | | |



| Storage and Handling | Storage | Storage should be in accordance with the instructions in Section 7 of the relevant material safety data sheet | | |
|-------------------------|---|---|--|--|
| | Shelf Life | 12 months in an unopened, original container from date of mixing at Cromadex centre | | |
| | Pack Size | 5 & 20 litres | | |
| Physical Properties | Volume Solids | 48 % mixed, dependent on colour | | |
| | Colour | Full range available including BS, RAL and special matches – all lead chromate free | | |
| | Gloss | Visual appearance will be affected by the fine texture additive | | |
| | Coverage | 19 m²/l @ 25 microns, assuming 100% transfer efficiency | | |
| | 440 Topcoat 05-44 Thinner 05-46 Thinner | VOC 428 g/l (dependent on colour) 769 g/l 867 g/l | Specific Gravity 1.10 (dependent on colour) 0.77 0.87 | |

Cromadex 440 Topcoat

atety Precautions and Disclaimer

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.

