

## Technical data sheet

<b>Date</b>	: Feb. 18, 2016
<b>Product name</b>	: <b>Interpon ACE 1000</b>
<b>Product code</b>	: <b>JE019QF (Formerly 30-2126)</b>
<b>Color</b>	: <b>Industrial Yellow – Interpon ACE 1000</b>
<b>Product Description</b>	: <b>Interpon ACE 1000</b> is a series of high durability polyester TGIC powder coatings designed for exterior exposure and for use as a decorative and/or functional coating for agricultural and construction equipment and components. <b>Interpon ACE 1000</b> coatings possess outstanding over bake resistance and excellent mechanical properties and provide significantly improved gloss retention and resistance to color change.

### Powder properties

<b>Type</b>	: Polyester TGIC
<b>Particle size</b>	: Suitable for electrostatic spray
<b>High Gloss (60°)</b>	: $\geq 80\%$
<b>Orange Peel</b>	: 6 min (ACT ref. Panels)
<b>Specific gravity</b>	: 1.34 +/-0.05 g/cm <sup>3</sup>
<b>Coverage at 1.0 mil</b>	: 143.5 sq.ft/lb/mil
<b>Storage conditions</b>	: Dry cool conditions (<80°F, <25°C)
<b>Shelf life</b>	: 12 months, typical
<b>Cure Schedule</b>	: 15-30 minutes at 355° F (180° C) 10-25 minutes at 375° F (190° C) 8-20 minutes at 390°F (200° C)

Failure to observe the correct curing conditions may cause difference in color, gloss and the deterioration of the coating properties.

### Test Conditions

<b>Substrate</b>	: Cold Rolled Steel
<b>Pretreatment</b>	: Iron Phosphate (B1000) or Zinc Phosphate (B952)
<b>Cure schedule</b>	: 15 minutes at 375°F (190°C) (object temperature)
<b>Film Thickness</b>	: 2.0-3.5 mils
<b>Testing condition</b>	: The results shown above are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

## Chemical tests

<b>Salt spray</b>	: DTM: 240 hours min; average creepback after scraping: < 3.0 mm	ASTM B117
<b>Cyclical Corrosion</b>	: DTM: 20 cycles/40 cycles if over ACE Primer Average creepback after scraping: <5.0 mm	SAE J2334
<b>Florida Exposure (12 mo.)</b>	: Gloss Retention (60°): $\geq 50\%$ Color Change ( $\Delta E$ ): < 4 max	ASTM D1014
<b>Humidity Resistance</b>	: No rust, no blisters, no gloss reduction after 1,000 hours	ASTM D2247
<b>Chemical Resistance</b>	: Good immersion resistance to water, diesel fuel, engine oil, gasoline & engine coolant.	ASTM D870
<b>Stability at Elevated temperatures</b>	: No significant change in color or gloss after 100% overbake.	

## Substrate pre-treatment


Aluminum, steel or Zinc surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminum substrates may require a chromate or non-chromate conversion coating.

## Application

**Interpon ACE 1000** powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance the product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. For more detailed information please contact an AkzoNobel technical service representative.

## Additional Information

**Interpon ACE 1000** high durability powder is an economical and environment friendly coating. Comparing to common outdoor use powder coating, it provides better anti-corrosion performance, color stability and gloss retention after exposure. In serious application environment, a primer is necessary. However, performance is still influenced by substrate & pretreatment type and film thickness uniformity.



## Safety Precautions

Please consult the Safety Datasheet (SDS).

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Safety Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.