

Product Data Sheet

AkzoNobel Powder Coatings

Interpon 610 MN119QF Shop Black

Product Description	<p>Interpon 610 is a range of polyester based powder coatings, formulated without TGIC, designed for exterior exposure, offering excellent light and weather resistance from a single coat finish. Interpon 610 powders are available in a wide range of colors in gloss, satin, matte and texture effect finishes and can be custom matched to customer specifications.</p>		
Powder Properties	Chemical type	Polyester TGIC Free	
	Appearance	Smooth	
	Gloss level (Gardner 60°)	42 - 52	
	Recommended Film thickness	3.0 – 5.0 mils	
	Specific gravity	1.51 +/-0.05 g/cm ³	
	Coverage @ 1.0 mil	127 sq.ft/lb/mil	
	Storage	Maximum 80°F	
	Shelf life	12 months, typical	
	Curing schedule (at object temperature)	20 minutes at 390F	
Mechanical Tests	Flexibility	ASTM D522M-17	1/8" mandrel
	Adhesion	ASTM D3359-17	5B, 100%
	Impact resistance (Dir/Rev)	ASTM 2794-93	60/40 in/lb min.
	Pencil Hardness	ASTM3363-05	2H (Scratch), 3H (Gouge) min.
Environmental and Durability Tests	Neutral Salt Spray	ASTM B117-16	<9/32" creep, at 336 hrs
	Humidity	ASTM D2247-15	No Change at 5000+ hours
	Xenon Weathering (800 hr.)	SAE J2527-17	Gloss Retention (60°): ≥ 70% Color Change (ΔE): < 3.0 max
	Exterior Durability		Yes
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.		
	Substrate	CRS or Aluminum	
	Pretreatment	Iron Phosphate (B1000) for CRS and chromate conversion for aluminum	
	Film thickness	2.0 – 3.0 mils	
	Cure schedule	20 minutes at 390°F	
	Actual film performance will depend on the individual circumstances in which the product is used.		
Pre-treatment	<p>Steel surfaces to be coated must be clean and free from grease. For maximum protection, it is essential to pre-treat components prior to the application of Interpon 610. Iron phosphate and zinc phosphate of ferrous metals improve corrosion resistance.</p> <p>Aluminum substrate may require a conversion coating.</p>		

Application	Interpon 610 powders can be applied by manual or automatic electronic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
Additional Information	Interpon 610 powders have no chalking and slight gloss loss after 12 months of South Florida exposure but no film breakdown or reduction in protective properties.
Key Product Attributes	
Safety Precautions	Please consult the Safety Datasheet (SDS).
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

<http://www.interpon.com/contact-us/>

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Product Name: **MN119QF**
Last Revision Date: **6-20-19**
Revision Number: **6**
Author: **R.LEBO**