

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A1243 AN110D

Product Description	Interpon A1243 for brake components combines toughness and durability with excellent corrosion and chemical resistance. They also come in a range of colors to meet the varied design needs for brake pads, brake discs, calipers and other wheel hardware that is visible in an open wheel design.		
Powder Properties	Chemical type	Epoxy	
	Area of usage	Automotive brake parts and engine blocks	
	Appearance	Smooth, matt	
	Gloss level (60°)	40 ± 10 GU	
	Colour	Black	
	Recommended Film Thickness (µm)	60 - 80	
	Density (g/cm³)	1.50 ± 0.05	
	Application	Electrostatic	
	Storage	Under dry, cool (<25°C) conditions	
	Shelf life	At least 24 months from production date	
Mechanical Tests	Curing schedule (at object temperature)	9 minutes at 200°C	
	Adhesion	DIN EN ISO 2409	Gt 0
	Impact resistance	ASTM D 2794	≥ 20 ip (reverse)
	Erichsen cupping	DIN EN ISO 1520	≥ 4 mm
Environmental and Durability Tests	Neutral Salt Spray	DIN EN ISO 7253	240 h Corrosion creep < 2 mm from scribe
	Humidity	DIN EN ISO 6270-2	240 h no blistering or loss of gloss
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.		
	Substrate	Steel panels, aluminium panels	
	Pretreatment	Bonder (LH) iron phosphate Bonder (722) yellow chromate	
	Film thickness	60 µm	
	Cure schedule	9 minutes at 200°C	
	Actual film performance will depend on the individual circumstances in which the product is used.		

Pre-treatment	Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of Interpon A1243 . Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate or chromate-free conversion pre-treatment.
Application	Interpon A1243 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
Safety Precautions	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

<http://www.interpon.com/contact-us/>

Copyright © 2017 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Interpon A1243 – AN110D - Issue #5

Last Revision Date: 27.06.2017

Author: E.T.Kok