

# Product Data Sheet

## AkzoNobel Powder Coatings

### Interpon 800

**Product Code: QL104Q (Formerly VT-401-C)**

**Product Description: ANSI 70 Gray**

<b>Product Description</b>	<p><b>Interpon 800</b> is a range of high durability TGIC powder coatings designed for exterior exposure. Tested against the most severe specifications, <b>Interpon 800</b> gives significantly improved gloss retention and resistance to color change. <b>Interpon 800</b> powders are available in a wide range of colors and glosses.</p>		
<b>Powder Properties</b>	<b>Chemical type</b>	Polyester TGIC	
	<b>Appearance</b>	Smooth	
	<b>Gloss level (Gardner 60°)</b>	65-75	
	<b>Recommended Film thickness</b>	3.0-5.0 Mils	
	<b>Specific gravity</b>	1.61 +/-0.05 g/cm <sup>3</sup>	
	<b>Coverage @ 1.0 mil</b>	119 sq. ft/lb/mil	
	<b>Storage</b>	Maximum 80°F	
	<b>Shelf life</b>	12 months, typical	
	<b>Curing schedule (at object temperature)</b>	30 minutes at 400°F.	
<b>Mechanical Test</b>	<b>Adhesion</b>	ASTM D3359	100%
	<b>Impact resistance (Direct)</b>	ASTM 2794	80 or better
	<b>Hardness</b>	ASTM3363	2H minimum
	<b>Abrasion Resistance</b>	ASTM D4060	Pass 3000 Cycles
<b>Environmental and Durability Tests</b>	<b>Neutral Salt Spray</b>	ASTM B117	Rating 6 at 1500 hours. No blisters
	<b>Humidity</b>	ASTM D2247	No Change at 1000 hours
	<b>Gravelometer</b>	SAE J4000	4B
	<b>SCAB</b>		15 Cycles
	<b>Humidity</b>		Yes
<b>Test Conditions</b>	<p>Testing has been determined under laboratory conditions using the following application properties and is for guidance only.</p>		
	<b>Substrate</b>	CRS	
	<b>Pretreatment</b>	Iron Phosphate (B1000)	
	<b>Film thickness</b>	3.0 – 5.0 mils	
	<b>Cure schedule</b>	30 minutes at 400°F	
	<p>Actual film performance will depend on the individual circumstances in which the product is used.</p>		
<b>Pre-treatment</b>	<p>Steel surfaces to be coated must be clean and free from grease. For maximum protection, it is essential to pre-treat components prior to the application of <b>Interpon 800</b> . Iron phosphate and zinc phosphate of ferrous metals improve corrosion resistance.</p>		

---

	Aluminum substrate may require a conversion coating.
<b>Application</b>	<b>Interpon 800</b> powders can be applied by manual or automatic electronic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
<b>Additional Information</b>	<b>Interpon 800</b> powders have up to 5 years of Florida exposure with good gloss and color stability.  Product meets IEEE C57.12.28-2005 Pad -Mounted Equipment-Enclosure Integrity and IEEE C 57. 12.31-2002 Pole-Mounted Equipment-Enclosure Integrity.
<b>Key Product Attributes</b>	Super Durable
<b>Safety Precautions</b>	Please consult the Safety Datasheet (SDS).
<b>Disclaimer</b>	<p><b>IMPORTANT NOTE:</b> The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

---

<http://www.interpon.com/contact-us/>

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Product Name: **Product Code: QI104Q**

Last Revision Date: **Date: 11/19/2018**

Revision Number: **#4**

Author: **Hummelm**