

Product Data Sheet

AkzoNobel Powder Coatings Interpon 600

Product Description

Interpon 600 is a series of polyester based powder coatings, formulated with TGIC, designed for the exterior environment, offering very good light and weather resistance.

Interpon 600 powders are available in a wide range of colours in gloss, satin, matt and textured effects and can be custom matched to the user's requirements.

Powder Properties

Chemical type	Polyester
Appearance	Depends on specific product
Particle Size	Suitable for electrostatic spray
Gloss	Depends on specific product
Specific gravity	1.2-1.8 g/cm ³ (depending on color)
Storage	Dry cool conditions below 30°C
Shelf life	6 months (<30°C), 12 months (<25°C)
Stoving schedule (object temperature)	10 minutes at 200°C Failure to observe the correct curing conditions may cause difference in colour, gloss and the deterioration of the coating properties.

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Mechanical tests: 0.6mm degreased steel
Pretreatment	Chemical and durability tests: Q-Al panel (A-36) Corrosion tests: Standard Zn-phosphating panel (GARDOBOND) or 0.6mm silane Q-Fe panel (R-36)
Film Thickness	60-80 microns
Stoving Schedule	10 minutes at 200°C (object temperature)

Mechanical Tests

Flexibility	ISO 1519	Pass 4mm
	GB/T 6742	Pass 4mm
Adhesion	ASTM D3359	5B
	ISO 2409	Gt 0
	GB/T 9286	Gt 0
Erichsen Cupping	ISO 1520	Pass >5mm
	GB/T 9753	Pass >5mm
Impact (direct)	ASTM D2794	>=50kg·cm
	GB/T 1732	50kg·cm
Pencil hardness*	ASTM D3363	>=F
	GB/T 6739	>=F

*The pencil used in hardness test is Mitsubishi pencil

Chemical and Durability Tests

Humidity	ASTM D1735	Pass-1000 hours, no blistering or loss of gloss
Distilled Water Immersion	ASTM D870	Pass-240 hours, no blistering or loss of gloss
Exterior Durability		Excellent-no chalking, slight loss of gloss after 12 months continuous exposure but no film breakdown or reduction in protective properties

Interpon600

	Chemical Resistance	Generally good resistance to most acids, alkalis and oils at ambient temperatures
Corrosion Tests**	Neutral Salt Spray ISO 9227 (Standard Zn-phosphating) Neutral Salt Spray ISO 9227 (Silane pretreatment)	Pass-800 hours, creep less than 2mm from scribe Pass-500 hours, creep less than 2mm from scribe
	<i>**Actual corrosion resistance is determined by substrate type, pretreatment effect, coating type and coating process and so on.</i>	
Pre-treatment	Aluminum, steel or Zintec surfaces to be coated must be clean and free from grease. Silane, ceramic, iron phosphate or lightweight zinc phosphate of ferrous metals improves corrosion resistance. Aluminum substrates may require a chromate conversion coating or chromium free passivation film.	
Application	Interpon 600 powders can be applied by manual or automatic electrostatic spray equipment, however for consistency of finish automatic equipment is preferred. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. Fluidizing air pressure ~0.7bar Transport air pressure ~0.7bar Recommended voltage 40-90kV	
Damage Repair	Surface preparation Sanding + Air Cleaning Application Recoat: Lower Voltage	
Safety Precautions	When using, do not eat, drink or smoke. Do not breathe the dust. In case of insufficient ventilation wear suitable respiratory equipment. For further information please refer to the specific product Material Safety Data Sheet (MSDS) available on request from your local AkzoNobel sales office.	
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>	

AkzoNobel (china) Investment Co., Ltd
22F, No.1788, West Nanjing Road, Jing'an District, Shanghai Tel: (86) 021 22205000
AkzoNobel Performance Coatings (Changzhou) Co., Ltd
No.1 Chunping Road, Binjiang Chemical Industrial Park, New District, Changzhou. Tel: (86) 0519 81065000
AkzoNobel Chang Cheng Coatings (Guangdong) Co., Ltd
Luotian Avenue, Songgang Town, Shenzhen. Tel: (86) 0755 27148450 Fax: (86) 0755 29936451
AkzoNobel Powder Coating (LangFang) Co., Ltd
No.32 Quanxing Road, LangFang Economic Development Area, Langfang. Tel: (86) 0316 5919519 Fax: (86) 0316 5919516
AkzoNobel Powder Coating (ChengDu) Co., Ltd
Checheng Road, East 4th, No.399, Longquanyi District, Chengdu. Tel: (86) 028 65708888 Fax: (86) 028 65708866
AkzoNobel Powder Coating (WuHan) Co., Ltd
No.89 Xinghua Road, Wuhan Economic Development Area, Wuhan. Tel: (86) 027 84256801 Fax: (86) 027 83564473

<http://www.interpon.com>

Copyright © 2021 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon 600 - Issue 4
Issued: 2014/11/1 Revision Date: 2021/12/13

Interpon[®]