

Product Data Sheet

Cromadex Liquid Coatings

Cromadex 222 Aerosol

One Pack Fast Air Drying Alkyd Topcoat Aerosol

Product Description

Cromadex 222 is a one pack fast air drying topcoat aerosol for touch up.

Fast drying

Available in 4 gloss levels

Exterior durable

Lead and chromate-free

Surface Preparation

The surface should be clean, dry and free of grease. Sound existing paintwork, including powder coating, should be degreased and abraded with P280 prior to painting.

Cromadex 222 aerosol can be applied over any Cromadex primer aerosol as well as many of the standard liquid primers in the Cromadex range. For further details regarding suitable primers and for larger scale finishing using Cromadex 222, please consult the Cromadex 222 datasheet.

Application Details

For touch up only

Ideal processing temperature: 15 - 25°C



Shake the aerosol for 2 minutes and spray a sample. Distance to the surface should be approximately 20 centimetres.

A choice of nozzles is available to suit your application. Please consult your local Cromadex Centre for details.

Apply in several thin layers. Between coats, re-shake aerosol.

Drying

Dust Dry After 5-10 minutes

Tack Free After 10-20 minutes

Hard Dry 2 hours

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the coating applied

Physical Properties

Coverage 1.5 – 2.0 m² per aerosol

VOC Approx 18% w/w

Shelf Life 6 months in an unopened, original container from date of mixing at Cromadex centre

Safety Precautions and Disclaimer

Before using this product please refer to the Cromadex Material Safety Data Sheet.

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.