

## Technical data sheet

<b>Date</b>	: 1-21-2017
<b>Product name</b>	: <b>Interpon A4000</b>
<b>Product Code</b>	: <b>JZ001Q (formerly 156C105-A)</b>
<b>Color</b>	: <b>Clear – Interpon A4000</b>
<b>Product Description</b>	: <b>Interpon A4000</b> is a series of clear powder coatings designed for OEM automotive wheel applications. They provide excellent smoothness and appearance, corrosion and chemical resistance and mechanical properties. <b>InterponA 4000</b> topcoats are known for their ease of application and have a long track record of performance on road wheels.

### Powder properties

<b>Type</b>	: Polyester TGIC
<b>Gloss</b>	: 155 – 175 UN
<b>Specific gravity</b>	: 1.22 +/-0.05
<b>Coverage at 1.0 mil</b>	: 157.6 sq.ft./lb./mil
<b>Storage</b>	: 80° F max
<b>Shelf life</b>	: 6 months
<b>Cure Schedule</b>	: 18 minutes at 375° F

### Test Conditions

<b>Substrate</b>	: Aluminium
<b>Pretreatment</b>	: Base Coat
<b>Cure schedule</b>	: 18 minutes at 375° F
<b>Dry film thickness</b>	: 1.8 – 2.3 mils
<b>Testing condition</b>	: The results shown above are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

### Mechanical tests

<b>Flexibility</b>	: 1/8" mandrel	ASTM D522
<b>Adhesion</b>	: 100%	ASTM D3359
<b>Hardness</b>	: H	ASTM D3363
<b>Impact (direct)</b>	: 80 inch-lbs	ASTM D2794
<b>Exterior Durability</b>	: Standard polyester durability	

## Substrate pre-treatment

Aluminum substrate must be clean and free from grease. For maximum protection, it is essential to pre-treat components prior to the application of **Interpon A4000** primers. OEM aluminum wheels, require a non-chromate conversion coating prior to application of **Interpon A4000** coatings.

## Application

**Interpon A4000** powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

## Additional Information

156C105-A holds the following Automotive OEM approvals:

**General Motors**

9985586

**Ford Motor**

ESA-M2P109-A

**Chrysler**

MS-PA6-7

## Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel