

Product Data Sheet

AkzoNobel Powder Coatings

Interpon D2525 Silky Texture – Y2305I La Boca

Product Description

Interpon D2525 Silky Texture Y2305I La Boca, is part of the Interpon D2525 Texture range, is a series of ultra-durable powder coatings combining a very fine sand-blasted aspect with a soft and warm feeling. **Interpon D2525 Silky Texture** specifically formulated without TGIC. It is intended for use on architectural aluminium and galvanized steel. Providing new levels of weathering resistance **Interpon D2525 Silky Texture** surpasses the performance of leading architectural powders. It offers significantly higher gloss retention and resistance to colour change combined with maximum film integrity to ensure long term cosmetic and functional protection.

These powder coatings are classified in Family I – class 6c under standard NFT 36-005.

Interpon D2525 Silky Texture meets the requirements of GSB Master, Qualicoat Class 2, EN 12206 (formerly BS6496), EN13438 (formerly BS6497:1984) and AAMA 2604.

Qualicoat Licence number: P-0643 (France), P-0877 (Italy), P-1252 (Turkey) under the brand name Interpon D2525 Textured

GSB Licence number: 183e (gloss 10) under the brand name Interpon D2525 Sablé

Powder Properties	Chemical type	Polyester	
	Appearance	Fine Texture	
	Gloss level	10±5 gloss units	
	Particle Size	Suitable for electrostatic spray	
	Specific gravity	1.24g/cm ³ ±0.03	
	Storage	Dry, cool conditions (open boxes must be resealed)	
	Shelf life	24 months below 30°C peak temperature 12 months below 35°C peak temperature	
	Curing schedule (at object temperature)	15-35 minutes at 180°C 12-25 minutes at 190°C 10-20 minutes at 200°C	
Mechanical Tests	Flexibility	ISO 1519 (Cylindrical mandrel)	Pass Qualicoat Class 2 requirements
	Adhesion	ISO 2409 (2mm crosshatch)	Pass Gt0
	Erichsen cupping	ISO 1520	Pass Qualicoat Class 2 requirements
	Impact resistance	ISO 6272	Pass Qualicoat Class 2 requirements
	Hardness	ISO 2815	> 80
Environmental and Durability Tests	Acetic Acid Salt Spray	ISO 9227	<16 mm ² corrosion/10cm (1000 hrs)

Constant Humidity	ISO 6270	No blistering, creep <1mm (1000 hrs)
Sulphur Dioxide	ISO 3231	Pass 30 cycles– no blistering, loss of gloss or discoloration
Permeability	Pressure Cooker EN12206-2004	Pass 1 hour, no blistering
Chemical Resistance		Generally good resistance to acids, alkalis and oils at normal temperatures
Mortar Resistance	EN12206-2004	No effect after 24 hours
Accelerated Weathering	ISO16474-2 (1000 hrs) ISO11507:1997 QUV B 313 (600 hrs)	>90% Gloss retention >50% Gloss retention
Exterior Durability	ISO 2810	Meets Qualicoat Class 2 requirements after 3 years Florida Meets AAMA 2604-13 requirements after 5 years Florida
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.	
	Substrate	Aluminium (0.5-0.8 mm Al Mg1)
	Pretreatment	Chrome free Qualicoat/GSB approved pretreatment
	Film thickness	70-90 microns (ISO 2360)
	Cure schedule	12 minutes at 200° C (object temperature)
	Actual film performance will depend on the individual circumstances in which the product is used.	
Pre-treatment	<p>For maximum protection it is essential to pretreat components prior to the application of Interpon D2525 Silky Texture.</p> <p>Aluminium components should receive a full multi-stage chromate conversion coating or suitable chrome-free pre-treatment or suitable pre-anodising to clean and condition the substrate. Detailed advice should be sought from the pre-treatment supplier.</p> <p>Interpon D2525 Silky Texture products may also be used on cast or mild steel. For outdoor use Interpon PZ anti-corrosive primer over a correctly prepared substrate is recommended</p>	
Application	<p>Interpon D2525 Silky Texture powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed up to a maximum of 20% using suitable equipment and recycled through the system. Please consult AkzoNobel for further details as to the correct mixing ratio for virgin/reclaim powder.</p> <p>Interpon D2525 Silky Texture powders should be applied at minimum 60µm.</p> <p>All powders can show small color differences from batch to batch, this is normal and unavoidable. While AkzoNobel take every precaution to minimize visible differences, this cannot be guaranteed. Applicators and fabricators are advised to use a single batch for parts that will be assembled together. Differences are more likely with special effect powders.</p> <p>Bonded products have better application properties than blended products (more stable)</p>	

but attention should still be paid to line settings in order to avoid “marble effect” and changes in aspect after recycling. For more information, it is suggested to read the *Metallic Applications Guidelines*.

Products with different codes should not be mixed even if same colour and gloss.

Post Application	For specific advice on the suitability of post coating processes such as bending or the use of sealants, adhesives, thermal break, cleaning etc. please consult AkzoNobel.
Maintenance	For specific advice on Cleaning and Maintenance, please consult the <i>Interpon D series Cleaning and Maintenance Guidelines</i> available from AkzoNobel.
Safety Precautions	Text as per local regulations
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

<http://www.interpon.com/contact-us/>

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Interpon D2525 Silky Texture Y2305I La Boca - Issue 2

Last Revision Date: 19/06/2018