

Product Data Sheet

AkzoNobel Powder Coatings Interpon ACE 2010 LE YL056F

Product Description

Interpon ACE 2010 LE is a series of superior UV and weather resistant TGIC-free polyester powder coatings designed for exterior exposure and for use as a decorative and/or functional coating for agricultural and construction equipment and components. Tested against the most severe specifications, **Interpon ACE 2010 LE** coatings offer the benefit of curing with lower oven temperature settings or increasing line speeds to improve throughput under normal temperature settings. These coatings also provide significantly improved gloss retention and resistance to color change and possess outstanding transfer efficiency and faraday cage penetration.

Powder Properties

Chemical type	Polyester super-durable (TGIC-free)
Area of usage	Exterior parts for agricultural machinery or construction equipment
Particle Size	Custom manufactured
Appearance	Smooth, glossy
Colour	Dark Grey CNH
Gloss (60°)	≥ 90 to ≤ 95 GU
Density (g/cm³)	1,30 ± 0,1
Stoving schedule	15 minutes at 160°C (time at object temperature) For further info about curing window please contact Akzo Nobel
Application	Electrostatic
Storage Stability	Under dry, cool (<25°C) conditions, at least 6 months from production date.

Test Conditions

The results are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Cold Rolled Steel
Pretreatment	Iron phosphate (B1000)
Film Thickness	70-90 µm
Cure Schedule	15 minutes at 160°C

Mechanical Tests

Adhesion	ASTM 3359	≥ 4B
Hardness	ASTM D3363	≥ 2H
Hardness Persoz	ASTM D4366 met.B	≥ 250
Impact	ASTM D2794	≥ 40 kg cm (reverse)
Elongation	ASTM D522 met.A	Max. elongation, no cracks or adhesion loss beyond 5mm from mandrel end

Corrosion and Chemical Tests

Salt Spray (1000 h)	ASTM B117 ASTM D1654, proc. A Method 2	Scribed, Rating 7
Cyclical Corrosion (5 Cycles)	CNH MTM0106 ASTM D1654, proc. A Method 2	Rating 9 min.

Interpon ACE 2010 LE YL056F

Corrosion and Chemical Tests

Humidity (600 h) (complete finish system)	ASTM D1735 ASTM D523 ASTM D1729 ASTM D714	10 min recovery Gloss Retention: 60° = 95% minimum 20° = 95% minimum No visual color change
Chemical Resistance (Exposure time, minimum)	CNH MTM0108	Gasoline = 1.0 h Diesel Fuel = 1.0 h Antifreeze (50:50) = 6 h Grease = 24 h Motor Oil = 24 h Diesel Engine Oil = 24 h Pesticide/Herbicide = TBD

Exterior Durability

Florida Exposure (24 months)	ASTM D1014	Gloss Retention: 60° = 75% minimum 20° = 45% minimum ΔE^* = 5.0 change, max.
--	------------	---

Additional information

Interpon ACE 2010 LE super durability powder is an economical and environment friendly coating. Comparing to common outdoor use powder coating, it provides better anti-corrosion performance, color stability and gloss retention after exposure. In serious application environment, a primer is necessary. However, performance is still influenced by substrate & pretreatment type and film thickness uniformity.

Pretreatment

Aluminum, steel or Zinc surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminum substrates may require a chromate or non-chromate conversion coating.

Application

Interpon ACE 2010 LE powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance the product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. For more detailed information please contact AKZO NOBEL technical service people.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924
PO Box 3 www.interpon.com
2170 BA Sassenheim
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon ACE 2010 – YL056F - Issue #4
Issued: 09.06.2010 Revision Date: 28.10.2015

Interpon®

**Interpon ACE 2010 LE
YL056F**

AkzoNobel Powder Coatings B.V. T +31 (0)71 308 6981
Rijksstraatweg 31 (building 24) F +31 (0)71 318 6924
PO Box 3 www.interpon.com
2170 BA Sassenheim
The Netherlands

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon ACE 2010 – YL056F - Issue #4
Issued: 09.06.2010 Revision Date: 28.10.2015

Interpon[®]