

Product Datasheet

Resicoat® R4-ES for Electrostatic Spray Application on Cold Surfaces Code: HJ601R

Product Description

Resicoat® R4-ES HJ601R is a high quality thermosetting epoxy powder coating for the corrosion protection of valves and fittings, manufactured from cast iron or steel. The powder coating is applied in one layer on cold surfaces by electrostatic spray application. The adhesion of Resicoat® R4-ES HJ601R to the metal substrate provides long term protection of the coated component. It ensures a reliable conservation to the function and value of the parts for the common water and gas distribution network. The applicator benefits from a modern and environmentally friendly process. Drinking water approvals are available.

	Typical value	Method
Powder Properties		
Binder system	Epoxy	
Density	1.30 – 1.40 g/cm ³	ISO 8130-2
Gel time at 200° C	25 – 40 sec.	modified ISO 8130-6
Particle size distribution	< 32 µm = 25 – 40 % < 125 µm > 98 %	Malvern ISO 8130-1
Storage stability	6 months from date of manufacture at ≤ 23° C	
Application Data		
Curing conditions	10 min., 190° C object temperature	
Material Properties		
Color	blue, ca. RAL 5015	
Recommended film thickness	120 – 220 µm	
Flow	smooth	
Gloss at 60° angle	70 – 100 units	ISO 2813
Cross cut	Gt 0	DIN EN ISO 2409
Drinking Water Approvals	DE: UBA-Coatings Guideline, Approval no.: K-301162-18, Hygiene Institut DE: DVGW directive work sheet W 270, Approval no.: W-279700k-17, Hygiene Institut FR: DGS/VS 4 No99/217, AFNOR XP P41-3, No. de dossier: ACS 18 MAT LY 183, LSEHL BE: Pipa/Hydrocheck 011, Certificat R4 dark blue, Belgaqua UK: BS 6920, Approval No. 1701509, WRAS	
Recommended Repair Material	Resicoat® RS two-component repair material	
Issue:	June 14, 2019	
Authorized by:	GK	
Revision no.:	12	

Disclaimer: This Product Data Sheet is based on the present state of our knowledge and on current laws. The data referring to Powder Properties, Application Data and Physical Tests is based on lab based samples. Factors such as quality or condition of the substrate may have an effect on the use and application of the product. It remains the responsibility of the user to test thoroughly if the product is applicable for the intended use. The use of the product beyond our recommendation releases us from our responsibility, unless we have recommended the specific use in writing. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. We are not liable for any application-technological advice. The Product Data Sheet shall be updated from time to time. Please ensure you have the latest version before using the product. All products and Product Data Sheets are subject to our standard terms and conditions of sale (GCS). You can receive the latest copy of GCS via internet or our post address. Brand names mentioned in this Product Data Sheet are trademarks of or are licensed to the AkzoNobel group.