

## Technical data sheet

<b>Date</b>	: 2/22/2011
<b>Product name</b>	: <b>Interpon TP</b>
<b>Product code</b>	: <b>4JC01QF</b>
<b>Color</b>	: <b>Blue – Interpon TP</b>
<b>Product Description</b>	: <b>Interpon TP 4JC01QF</b> is a melt-mixed nylon powder coating which has excellent abrasion and wear resistance, good chemical and solvent resistance, good exterior durability, a low coefficient of friction, and excellent machinability. Durable and easy to clean, typical applications for <b>4JC01QF</b> include automotive clips and wear surfaces, office and institutional furniture, industrial pipe and fittings, food processing and handling equipment, marine hardware, and shopping carts. Please consult your AkzoNobel Powder Coatings technical representative to ensure that the selected product is suitable for your end use application.

### Powder properties

<b>Type</b>	: Nylon
<b>Cure Schedule</b>	: Preheat 650F/6 min Postheat 475F/1 min
<b>Recommended Film Thickness</b>	: 10-12 mils
<b>Application Method</b>	: Fluid Bed
<b>Specific Gravity</b>	: 1.13 +/-0.05 g/cm <sup>3</sup>
<b>Coverage at 1.0 mil</b>	: 170.17 sq.ft/lb/mil
<b>Gloss (60°)</b>	: 40-80
<b>Shelf Life</b>	: 12 months, typical

### Typical performance characteristics

<b>Hardness, Shore D</b>	: 70-80	ASTM D2240
<b>Tensile Strength</b>	: 6000psi	ASTM D638
<b>Melting Point</b>	: 356-374F (180-190C)	ASTM D789
<b>Salt spray</b>	: 1000+ hours – “x” scribe	ASTM B117
<b>Dielectric Strength</b>	: 800-1200 volts/mil	ASTM D149
<b>Elongation</b>	: 15%	ASTM D638
<b>Taber Abrasion</b>	: 8-18mg loss	ASTM D4060

### Substrate pre-treatment

All oil and grease, mill scale and rust, must be removed. Iron or Zinc phosphate pretreatment is recommended for optimum performance.

### Application

Water quench is recommended to increase gloss and maximize physical properties. A surfactant (wetting agent) should be added to prevent spotting.

## Safety Precautions

Please consult the Safety Datasheet (SDS).

### **FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Safety Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.