

Product Datasheet



BU Powder Coatings

Interpon 700 TEX RAVEN BLACK

Code: EN327N

Product Description: Interpon 700 TEX RAVEN BLACK is a texture finish epoxy polyester powder coating, offering good colour, light and heat stability. When applied with right equipments and expertise, this powder provides excellent texture effect for aesthetic appeal as well as coverage.

This powder is compliant with ROHS directive, 2002/95/EC.

| | Result | Method |
|---------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------|
| Powder Properties: | Colour | Black |
| | Gloss(60° ahead) | 7-9 |
| | Specific Gravity | 1.5-1.7 g/cm ³ |
| | Particle size | Suitable for electrostatic spray |
| | Storage | Keep in dry and cool conditions, away from direct sunlight |
| | Shelf Life | 12 months when stored in sealed carton as per above conditions |
| Test Conditions | The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used. | |
| Mechanical and Chemical Test : | Substrate | Mild Steel |
| | Pre-treatment | Zinc Phosphate |
| | Film Thickness | 50-70 microns |
| | Stoving | 10 minutes at 180°C (EMT) |
| | Adhesion | GT=0 |
| | Scratch Hardness | 2 kg |
| | Flexibility (Conical Mandrel) | 6 mm |
| | Erichsen Cupping | 4 mm |
| | Impact | 100 kg.cm |
| | Salt Spray | <3 mm corrosion creep from scribe after 500 hrs exposure in SST cabinet |
| | Humidity Chamber | No blistering, no colour change after 500 hrs exposure in Humidity cabinet |
| Pre-treatment: | For more information regarding specific substrates and applications for Interpon 700 TEX RAVEN BLACK contact AkzoNobel. | |
| Application: | Interpon 700 TEX RAVEN BLACK can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. | |
| Safety Precautions: | When using do not eat, drink or smoke. Do not breathe the dust. In case of insufficient ventilation wear suitable respiratory equipment. For further information please refer to the specific product Material Safety Data Sheet (MSDS – PC010). | |

AkzoNobel India Limited, Bangalore 562114 India Tel +91 80 22895000 Fax +91 80 22895500 www.interpon.com

Copyright ©2004 AkzoNobel India Ltd. Interpon is a registered trademark of AkzoNobel

Code – Issue 3

Issued: January 2015 PM/TDS/0222

Disclaimer: The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Interpon
powder coatings
EVERY COLOR IS GREEN