

Product Datasheet

AkzoNobel



BU Powder Coatings Interpon 700 NEW P.O RED Code: EG043N

Product Description: Interpon 700 NEW P.O RED is a smooth finish epoxy polyester powder coating, offering good colour, light and heat stability. When applied with right equipments and expertise, this powder provides excellent flow and finish effect for aesthetic appeal as well as coverage.

This powder is compliant with ROHS directive, 2002/95/EC.

	Result	Method
Powder Properties:		
Colour	Red	
Gloss(60° ahead)	85±5	ASTM D523-89
Specific Gravity	1.5-1.7 g/cm ³	Theoretical
Particle size		Suitable for electrostatic spray
Storage		Keep in dry and cool conditions, away from direct sunlight
Shelf Life		12 months when stored in sealed carton as per above conditions

Test Conditions The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Mechanical and Chemical Test :	Substrate	Mild Steel	
	Pre-treatment	Zinc Phosphate	
	Film Thickness	60-80 microns	ASTM D 1186-93
	Stoving	10 minutes at 180°C (EMT)	
	Adhesion	GT=0	ASTM D 3359 -97
	Scratch Hardness	2 kg	ASTM D 1474-92
	Flexibility (Conical Mandrel)	6 mm	ASTM D522 –93A
	Erichsen Cupping	6 mm	ASTM 643-84
	Impact (Direct)	50 kg.cm	ASTM D2794
	Salt Spray	<3 mm corrosion creep from scribe after 500 hrs exposure in SST cabinet	ASTM B-117
	Humidity Chamber	No blistering, no colour change after 500 hrs exposure in Humidity cabinet	ASTM D2247

Pre-treatment: For more information regarding specific substrates and applications for Interpon 700 NEW P.O RED contact AkzoNobel.

Application: Interpon 700 NEW P.O RED can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions: When using do not eat, drink or smoke. Do not breathe the dust. In case of insufficient ventilation wear suitable respiratory equipment. For further information please refer to the specific product Material Safety Data Sheet (MSDS – PC010).

AkzoNobel India Limited, Bangalore 562114 India Tel +91 80 22895000 Fax +91 80 22895500 www.interpon.com
Copyright ©2004 AkzoNobel India Ltd. Interpon is a registered trademark of AkzoNobel
Code – Issue 1

Issued: June 2015 PM/TDS/1069

Disclaimer: The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Interpon
powder coatings
EVERY COLOR IS GREEN