

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A4742 YZ204QF LOW GLOSS CLEAR

Product Description	The line of Interpon A4742 polyester clearcoats (TGIC free) stand ready with excellent appearance and performance. Together they are perfectly balanced to provide long lasting protection from chipping, scratching, wheel cleaners and corrosive road environments. Interpon A4742 clears have more than 20 years of commercial success that make them the topcoat of choice for aluminum wheels.		
Powder Properties	Chemical type	Polyester	
	Area of usage	Automotive	
	Appearance	Smooth, clear	
	Gloss 60°	5.0 – 15.0 gloss units	
	Recommended Film Thickness on Wheels	2.5 – 3.5 mils	
	Density (g/cm³)	1.20 ± 0.05	
	Application	Electrostatic	
	Storage	Under dry, cool (≤70°F) conditions	
	Shelf life	At least 6 months from production date	
	Curing schedule (at object temperature)	20 minutes at 375°F	
Mechanical Tests	Adhesion	ASTM D3359	100%
	Impact resistance	ASTM D 2794	≥ 80 ip (reverse)
Environmental and Durability Tests	Neutral Salt Spray	ASTM B117	240h corrosion creep < 2mm from scribe
	Humidity	ASTMD1735-14	240h no blistering or loss of gloss
	Exterior		Yes
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.		
	Substrate	Aluminum	
	Pretreatment	Chromate Free conversion or Chromate	
	Film thickness	2.5 -3.5 mils	
	Cure schedule	20 minutes at 375°F	
	Actual film performance will depend on the individual circumstances in which the product is used.		
Pre-treatment	Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of Interpon A4742 . Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate or chromate-free conversion pre-treatment.		

Application	Interpon A4742 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
--------------------	---

Safety Precautions	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.
---------------------------	--

Disclaimer	IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give, or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.
-------------------	--

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied, and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

<http://www.interpon.com/contact-us/>

Copyright © 2019 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Interpon A4742 – YZ204QF – Issue # 2

Last Revision Date: 12/21/21