Product Datasheet



BU Powder Coatings

Interpon D1036 RAL 8016 BROWN

Code: SM226N

Product Description: Interpon D1036 RAL 8016 BROWN is a smooth finish Standard Durable powder coating specifically formulated for use on architectural aluminum components. Interpon D1036 RAL 8016 BROWN gives excellent exterior durability, color and gloss retention.

| | | Result | Method |
|---------------------|---|--|--|
| Powder Properties: | Colour | Brown | |
| | Gloss (60° ahead) | 20-30 | ASTM D523-89 |
| | Specific Gravity | 1.5-1.7 g/cm³ | Theoretical |
| | Particle size | | Suitable for electrostatic spray |
| | Storage | | Keep in dry & cool conditions away from direct sunlight |
| | Shelf life | | 12 Months when stored in sealed carton as per above conditions |
| Test Conditions | The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used. | | |
| Mechanical and | | | |
| Chemical Test : | Substrate | Aluminium (AlMg 1 0.8mm) | |
| | Pre-treatment | Chromate | 10TH B 1100 00 |
| | Film Thickness | 60-80 microns | ASTM D 1186-93 |
| | Stoving | 10 minutes at 200°C (EMT) | |
| | Adhesion | GT=0 | ASTM D 3359 -97 |
| | Scratch Hardness | 3 kg | ASTM D 1474-92 |
| | Flexibility (Conical Mandrel) | 5 mm | ASTM D522 –93A |
| | Erichsen Cupping | 5 mm | ASTM 643-84 |
| | Impact | 25 kg .cm | ASTM D2794 |
| | Salt Spray | <3 mm corrosion creep from scribe after 1000 hrs exposure in SST cabinet Minimum blister rating 8 | ASTM B-117, ASTM D1654 |
| | Exterior Durability | No chalking or loss of adhesion after tape pull and only slight chalking and fading. | 12 Months Florida Exposure |
| Pre-treatment: | For more information regarding specific substrates and applications for Interpon D1036 RAL 8016 BROWN contact AkzoNobel. | | |
| Application: | Interpon D1036 RAL 8016 BROWN can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system. | | |
| Safety Precautions: | When using do not eat, drink or smoke. Do not breathe the dust. In case of insufficient ventilation wear suitable respiratory equipment. For further information please refer to the specific product Material Safety Data Sheet (MSDS – PC010). | | |

AkzoNobel India Limited, Bangalore 562114, India. Tel +91 80 22895000 Fax +91 80 22895500 www.interpon.com Copyright ©2004 AkzoNobel India Ltd. Interpon is a registered trademark of AkzoNobel

Issued: January 2015
Disclaimer: The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

