

Technical Datasheet

Interpon 310

MWB00F

Polyester powder coatings for indoor applications



Product description

Interpon 310 is a series of polyester resin based thermo-setting powder coatings, without TGIC. **The Interpon 310** resin system is warning label free. The pigments used in the Interpon 310 series restrict the field of application of this powder coatings class to interior uses. **Interpon 310** is designed for interior decoration such as, metal furniture, shop fittings, shelves, light fittings.

Powder properties

	Typical value
Chemical Type	Polyester – TGIC Free
Appearance	Coarse Texture
Color	LUTETIUM
Density	1.45 - 1.55 g/cm ³
Finish Effect	Dry-blended
Recommended film thickness	60 - 90 µm
Shelf life	24 months below 30 °C
Storage Conditions	Under dry, cool ($\leq 30^{\circ}\text{C}$) conditions (open boxes must be resealed)
Curing schedule	8-16 min at 200°C 10-20 min at 180°C 20-40min at 170°C (at object temperature)

Pre-treatment

Aluminium components should receive a full multi-stage chromate conversion coating or suitable chrome-free pre-treatment or suitable pre-anodising to clean and condition the substrate. Detailed advice should be sought from the pre-treatment supplier. Iron phosphate and particularly Zinc phosphating of ferrous metals improves corrosion resistance. Aluminium substrates may require a chromate conversion coating.

Application

All powders can show small color differences from batch to batch, this is normal and unavoidable.
Bonded products have better application properties than blended products (more stable) but attention should still be paid to line settings in order to avoid “marble effect” and changes in aspect after recycling.
Products with different codes should not be mixed even if same colour and gloss.
A good protection is linked with the recommended film thickness.
Powders can be applied by manual or automatic electrostatic spray equipment.

Interpon 310 powder coatings can be applied by corona electrostatic or tribostatic equipment. However, the aspect obtained by tribo-static equipment may vary when compared to electrostatic application and/or our color card.

Application Method	(depends on the product, please consult Akzo Nobel for more information), Electrostatic, Tribo
Recycling	Not recommended.

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V1, 17.06.2025

Region: EMEA

AkzoNobel

Technical Datasheet

Interpon 310

MWB00F

Polyester powder coatings for indoor applications



Post application

Contact, even for a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on this coating.

Test conditions

Actual product performance will depend upon the circumstances under which the product is used. Testing has been determined under laboratory conditions using the following application properties and is for guidance only.

Pre-treatment	Zinc Phosphate
Substrate	Polished steel
Curing schedule	12 min at 200°C (object temperature)
Film Thickness	60 - 70 µm

Mechanical tests

	Typical value	Method/standard
Adhesion	Class 0	ISO 2409 (2 mm Crosshatch)
Erichsen cupping	Pass 5 mm	ISO 1520
Flexibility	Pass 5 mm	ISO 1519
Hardness	Pass - no penetration to substrate	ISO 1518-1 (2000g)
Impact resistance	≥30 kg.cm	ISO 6272-2 (d)

Chemical and durability tests

Whilst maintaining the general protective and anti-corrosive properties of powder coatings, aluminum and copper/bronze metallic finishes, when submitted to the listed tests, may rapidly show a loss of metallic aspect. The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.

	Typical value	Method/standard
Salt spray test	Pass, no corrosion creep more than 3 mm from scribe, 500 h, Steel Panels 0,8 mm	ISO 9227
Water immersion	Pass - no blistering	

Environmental and durability tests

	Typical value	Method/standard
Humidity	Pass - no blistering, 1000 h	ISO 6270-2 CH (Constant humidity)
Exterior durability	Some chalking and loss of gloss after 3-6 months continuous outdoor exposure. Protective properties retained. Not recommended for outdoor applications.	

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V1, 17.06.2025

Region: EMEA

AkzoNobel

Technical Datasheet

Interpon 310

MWB00F

Polyester powder coatings for indoor applications



Maintenance

For specific advice on Cleaning and Maintenance, please follow Powder Coatings: Cleaning & Maintenance of Surfaces for Industrial use available from AkzoNobel.

Repair

Surface preparation

Damaged areas must be clean and free of grease or rust. Dry-sand the area with 600 grade paper down to the substrate. The area must be completely free of dust and cleaned with a non-aggressive solvent before proceeding.
Any damage of the coating system must be repaired as soon as possible.

Application

For repairs a PU (2K or 1K) liquid paint is recommended.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V1, 17.06.2025

Region: EMEA

AkzoNobel