

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A2205

QN304U

FORD YGYA BLACK TEXTURE

Product Description	Interpon A2205 offer enhanced exterior durability while our textured low gloss products provide a uniform finish that is both rugged and refined. Interpon A2205 powders are super-durable (> two years Florida) and answer to the requested performance level specified by the OEMs.		
Powder Properties	Chemical type	Polyester-TGIC super durable	
	Area of usage	Automotive trim parts	
	Appearance	Fine texture	
	Gloss level (60°)	2.0 – 4.0 UNITS	
	Colour	Black Texture	
	Recommended Film Thickness (mils)	2.5 – 3.5 mils	
	Density (g/cm³)	1,60 ± 0,05	
	Coverage at 1.0 mil	120 sq.ft/lb/mil	
	Application	Electrostatic	
	Storage	Under dry, cool (< 80°F) conditions	
Shelf life	At least 12 months from production		
	Curing schedule (at object temperature)	20 minutes at 375°F	
Mechanical Tests	Adhesion	ASTM D3359	100%
	Flexibility	ASTM D522	¼" Mandrel
	Hardness	ASTM D3363	H-2H min
	Impact resistance	ASTM D2794	80-120 ip (direct)
	Impact resistance	ASTM D 2794	80-120 ip (reverse)
Environmental and Durability Tests	Neutral Salt Spray	ASTM B117	> 240 h corrosion creep < 2 mm from scribe
	Humidity	ASTM D2247	> 240 h no blistering or loss of gloss
	Artificial Weathering	Xenon SAE2527?	xxxxxx
OEM Approvals	DAIMLER CHRYSLER:	MS-PE-16-2	
	FORD MOTOR:	WSS-M70J5B	

Test Conditions	<p>Testing has been determined under laboratory conditions using the following application properties and is for guidance only.</p> <p>Substrate Cold Rolled Steel</p> <p>Pretreatment Iron Phosphate (B1000), Zinc Phosphate (B952), Electrocoat</p> <p>Film thickness 2.5 – 3.5 mils</p> <p>Cure schedule 20 minutes at 375°F</p> <p>Actual film performance will depend on the individual circumstances in which the product is used.</p>
Pre-treatment	<p>Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of Interpon A2205. Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate or chromate-free conversion pre-treatment.</p>
Application	<p>Interpon A2205 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.</p>
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

<http://www.interpon.com/contact-us/>

Copyright © 2017 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Product Name: QN304U
 Last Revision Date: 10-5-18
 Revision Number: 2
 Author: R.LEBO