

Product Data Sheet

AkzoNobel Powder Coatings

Interpon A2203 Q2301QF

Product Description	Interpon A2203 powders can be used for pillars and appliqué, roof racks, grille guards, bumpers, hitches, mirror housings, and wiper arms all require protection from the environment as well as being visually harmonious with the overall design of a vehicle. Interpon A2203 powders are super durable metallic (> two years Florida) and answer to the requested performance level specified by the OEMs.		
Powder Properties	Chemical type	TGIC POLYESTER	
	Area of usage	EXTERIOR TRIM	
	Appearance	FINE TEXTURE	
	Gloss level (60°)	2.0 – 5.0	
	Colour	MATTE VAPOR	
	Recommended Film Thickness (mils)	2.5 – 3.5	
	Density (g/cm³)	1.46 +/-0.05	
	Coverage (ft²/lb/mil)	132	
	Storage	MAXIMUM 80°F	
	Shelf life	12 MONTHS, TYPICAL	
	Curing schedule (at object temperature)	10 MINUTES AT 375°F	
Mechanical Tests	Adhesion	ASTM D3359	100%
	Erichsen cupping	N/A	
	Impact resistance	ASTM D2794	140/160MIN
	Hardness	ASTM D3363	F-2H
Environmental and Durability Tests	Neutral Salt Spray	ASTM B117	240 HOURS
	Humidity	ASTM D2247	240 HOURS
	Exterior	YES	
OEM Approvals	OEM		
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.		
	Substrate	COLD ROLLED STEEL	
	Pretreatment	IRON PHOSPHATE (B1000), ZINC PHOSPHATE (B952), ELECTROCOAT	
	Film thickness	2.0 – 3.0	
	Cure schedule	10 MINUTES AT 400°F	
	Actual film performance will depend on the individual circumstances in which the product is used.		

Pre-treatment	Steel surfaces to be coated must be clean and free from grease. For maximum protection it is essential to pre-treat components prior to the application of Interpon A2203 . Iron Phosphate and Zinc Phosphate of ferrous metals improve corrosion resistance. Aluminium parts require a chromate or chromate-free conversion pre-treatment.
Application	Interpon A2203 powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that for consistent application and appearance product be fluidized during application. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
Additional information	
Safety Precautions	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.
Disclaimer	<p>IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.</p> <p>Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.</p> <p>Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel</p>

<http://www.interpon.com/contact-us/>

Copyright © 2017 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Interpon A2203 – Q2301QF - Issue #2

Last Revision Date: 2/7/2020

Author: WILLOW SLUSSER