

# Product Data Sheet

## Cromadex Liquid Coatings

### Cromadex 232 Topcoat

### One Pack Air Drying Alkyd Medium Texture Topcoat

#### Product Description

Cromadex 232 is a one pack air drying medium texture topcoat. The product has a long wet edge that enables a seamless finish on large articles without dry spray.

Cromadex 232 is available in the full Cromadex range of colours, including BS, RAL and special matches all in a lead free finish.

#### Extra Life

Life expectancy of up to 7 years in a C2\* environment when used with a suitable Cromadex primer. See Extra Life brochure for full details.

\* as determined in ISO12944: 2018

#### Products and Ancillaries

232 Topcoat  
05-46 Thinner (Standard)  
85-72 Thinner (Slow)

#### Suitable Substrates and Preparation

<b>Mild Steel</b>	Degrease with Cromadex 678 Spirit Wipe and abrade steel with P180. If necessary blast clean to remove millscale, minimum surface preparation SA2. Apply suitable Cromadex primer
<b>Aluminium &amp; Galvanised Steel</b>	Apply Cromadex 903 Chromate-Free Etch Primer (then other Cromadex primer is required to increase film build)
<b>Stainless Steel</b>	Use of Cromadex 903, AQ58, 750 or 850 primer is required

#### Application Details

<b>Thinning Ratio</b>	5 parts 232 Topcoat 1 part Thinner (dependent on application equipment)	
<b>Spraying Viscosity</b>	45 – 65 seconds ISO Cup4 @ 20°C 25 – 30 seconds BS 4 Cup @ 20°C	
<b>Approved Thickness</b>	25 – 35 microns DFT	50 – 70 microns WFT
<b>Spray Gun</b>	<b>Fluid tip size</b>	<b>Working pressure</b>
<i>Conventional</i>	1.4 – 1.8 mm	3.5 – 4.2 bar
<i>Suction Feed HVLP</i>	1.4 – 1.8 mm	0.7 bar (max)
<i>Pressure Pot HVLP</i>	1.0 – 1.4 mm	0.7 bar (max)
<i>Other Methods</i>	Not suitable	

#### Drying and Overcoating

Substrate Temperature	Drying Times		Overcoating Times	
	Touch Dry	Through Dry	Minimum	Maximum
20°C	3 hours	17 hours	Not recommended	
35°C	150 mins	15 hours	Not recommended	
<b>Force Drying</b>	Flash-off for 10-15 mins, then 60-80°C for 30 mins			
<b>Stoving</b>	Not recommended			
<b>Full Properties</b>	7 days			

# Cromadex 232 Topcoat

## Storage and Handling

<b>Storage</b>	Storage should be in accordance with the instructions in Section 7 of the relevant material safety data sheet
<b>Shelf Life</b>	12 months in an unopened, original container from date of mixing at Cromadex centre
<b>Pack Size</b>	5 & 20 litres

## Physical Properties

<b>Volume Solids</b>	49 % mixed, dependent on colour	
<b>Colour</b>	Full range available including BS, RAL and special matches – all lead chromate free	
<b>Gloss</b>	Visual appearance will be affected by the medium texture additive	
<b>Coverage</b>	20 m <sup>2</sup> /l @ 25 microns, assuming 100% transfer efficiency	
	<b>VOC</b>	<b>Specific Gravity</b>
<b>232 Topcoat</b>	428 g/l (dependent on colour)	1.10 (dependent on colour)
<b>05-46 Thinner</b>	867 g/l	0.87
<b>85-72 Thinner</b>	870 g/l	0.87

## Safety Precautions and Disclaimer

### Before using this product please refer to the Cromadex Material Safety Data Sheet.

The information contained in this data sheet is not intended to be exhaustive, and any person using the product without first obtaining written confirmation from us as to the suitability of the product for the intended purposes, does so at their own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability whatsoever arising from the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this data sheet is current prior to using the product.