

Product Datasheet



BU Powder Coatings Interpon D1036 METRO GOLD Code: SWC39N

Product Description: Interpon D1036 METRO GOLD is a smooth finish **Standard Durable** powder coating specifically formulated for use on architectural aluminum components. Interpon **D1036 METRO GOLD** gives excellent exterior durability, color and gloss retention.

	Result	Method
Powder Properties:		
Colour	Metallic	
Gloss (60° ahead)	NA	ASTM D523-89
Specific Gravity	1.5-1.7 g/cm ³	Theoretical
Particle size		Suitable for electrostatic spray
Storage		Keep in dry & cool conditions away from direct sunlight
Shelf life		12 Months when stored in sealed carton as per above conditions

Test Conditions The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Mechanical and Chemical Test :		
Substrate	Aluminium (AlMg 1 0.8mm)	
Pre-treatment	Chromate	
Film Thickness	60-80 microns	ASTM D 1186-93
Stoving	10 minutes at 200°C (EMT)	
Adhesion	GT=0	ASTM D 3359 -97
Scratch Hardness	3 kg	ASTM D 1474-92
Flexibility (Conical Mandrel)	5 mm	ASTM D 522 –93A
Erichsen Cupping	5 mm	ASTM 643-84
Impact	25 kg .cm	ASTM D 2794
Salt Spray	<3 mm corrosion creep from scribe after 1000 hrs exposure in SST cabinet Minimum blister rating 8	ASTM B-117, ASTM D1654
Exterior Durability	No chalking or loss of adhesion after tape pull and only slight chalking and fading.	12 Months Florida Exposure

Pre-treatment: For more information regarding specific substrates and applications for **Interpon D1036 METRO GOLD** contact AkzoNobel.

Application: Interpon **D1036 METRO GOLD** can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Safety Precautions: When using do not eat, drink or smoke. Do not breathe the dust. In case of insufficient ventilation wear suitable respiratory equipment. For further information please refer to the specific product Material Safety Data Sheet (MSDS – PC010).

AkzoNobel India Limited, Bangalore 562114, India. Tel +91 80 22895000 Fax +91 80 22895500 www.interpon.com

Copyright ©2004 AkzoNobel India Ltd. Interpon is a registered trademark of AkzoNobel

Code – Issue 3

Issued: November 2014

Disclaimer: The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Interpon
powder coatings
EVERY COLOR IS GREEN