

## **Product Data Sheet**

**AkzoNobel Powder Coatings** 

## INTERPON ACE PRIMER AE101Q YELLOW

Product Description	Interpon 100 is a series of epoxy protection and chemical resistance Interpon 100 is designed for interin gloss, satin, matte, and texture	e when applied over a proior application only. <b>Inter</b>	perly prepared metal substrate.  pon 100 powders are available
Powder Properties	Chemical type	Ероху	
	Appearance	Smooth	
	Gloss level (Gardner 60°)	55-75	
	Recommended Film thickness	2.0 – 3.0	
	Specific gravity	1.54 +/-0.05 g/cm <sup>3</sup>	
	Coverage @ 1.0 mil	124.9 sq.ft/lb/mil	
	Storage	Maximum 80°F	
	Shelf life	6 months	
	Curing schedule (at object temperature)	7 minutes at 375°F	
Mechanical Tests	Flexibility	ASTM D522	1/8" mandrel
	Adhesion	ASTM D3359	100%
	Impact resistance (Direct)	ASTM 2794	80/80
	Hardness	ASTM3363	5H
Environmental and Durability Tests	Neutral Salt Spray	ASTM B117	<1/8" creep, no blisters, 1,000 hrs
	Humidity	ASTM D2247	No Change at 1000 hours
	Exterior Durability		No
Test Conditions	Testing has been determined under laboratory conditions using the following application properties and is for guidance only.		
	Substrate	CRS	
	Pretreatment	Iron Phosphate	
	Film thickness	2.0 – 3.0 mils	
	Cure schedule	7 minutes at 375°F	
	Actual film performance will depend on the individiual circumstances in which the product is used.		
Pre-treatment	Steel surfaces to be coated must it is essential to pre-treat comports phosphate and zinc phosphate of	onents prior to the appli	ication of Interpon 100. Iron
Application	Interpon 100 powders can be applit is recommended that for consist during application. Unused powde through the coating system.	ent application and appea	arance product be fluidized

AE101Q Page 1 of 2



Additional Information	This product is sensitive to heat. Please store out of direct sunlight and in climate controlled environment.	
Key Product Attributes		
Safety Precautions	Please consult the Safety Datasheet (SDS).	
Disclaimer	IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.  Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.  Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel	
	Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel	

## http://www.interpon.com/contact-us/

Copyright © 2010 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Product Name: AE101Q Last Revision Date: 8/31/2020

Revision Number: 3

Author: D.Fraccica

AE101Q Page 2 of 2