

Technical Datasheet

Interpon 610 Low-E

Low cure polyester powder coating for outdoor use



Product description

Interpon 610 Low-E is a range of polyester based powder coatings, formulated without the use of TGIC. This range is designed for either interior or exterior environment, offering excellent light and weather resistance on a variety of substrates. The products in the range are engineered to minimize the formation defects such as pinholes caused by air bubbles in the paint film due to gas release in porous substrates during curing*.

The cured coating shows no blooming effect. They are also easy to apply and can be cured from 150-170°C thereby offering potential energy reductions during the cure process.

Approvals

Resistance to Fire Approval A2,s1,d0 with film thickness up to 120 µm (generic polyester 600) according to EN13501-1

Powder properties

	Typical value
Chemical Type	Polyester – TGIC Free
Density	1.2 - 1.9 g/cm ³ , depending on colour and effect
Recommended film thickness	60 - 110µm
Shelf life	24 months below 25 °C
Storage Conditions	Under dry, cool (≤ 25°C) conditions (open boxes must be resealed)
Curing schedule	23-35 min at 150°C 12-30 min at 160°C 8-20 min at 170°C 5-10 min at 180°C (at object temperature)

Pre-treatment

Galvanised steel requires surface preparation by either multi-stage pretreatment using either zinc phosphate or chromate conversion or controlled sweep blasting. Depending on the type of galvanizing, degassing or use of anti-bubbling additives may be required – follow the procedural advice of the pretreatment supplier.

Iron phosphate and particularly Zinc phosphating of ferrous metals improves corrosion resistance. Aluminium substrates may require a chromate conversion coating.

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V5, 25.05.2024

Region: EMEA

AkzoNobel

Technical Datasheet

Interpon 610 Low-E

Low cure polyester powder coating for outdoor use



Application

Powders can be applied by manual or automatic electrostatic spray equipment.

A good protection is linked with the recommended film thickness.

All powders can show small color differences from batch to batch, this is normal and unavoidable.

Applicators and fabricators are advised to use a single batch for parts that will be assembled together. Differences are more likely with special effect powders.

Bonded products have better application properties than blended products (more stable) but attention should still be paid to line settings in order to avoid "marble effect" and changes in aspect after recycling.

Different substrates (aluminium, steel, galvanized steel...), use of primer, and big changes in film thickness may give a different aspect.

Products with different codes should not be mixed even if same colour and gloss.

It is recommended that for consistent application and appearance product be fluidized during application.

Coarse texture finished should be applied at minimum 80µm.

Application Method	Tribo, Electrostatic
Recycling	Please consult AkzoNobel for further details as to the correct mixing ratio for virgin/reclaim powder. Unused powder can be reclaimed using suitable equipment and recycled through the coating system, but a minimum of 70% virgin powder should be used. For solid shades, unused powder can be reclaimed

Post application

For specific advice on the suitability of post coating processes such as bending or the use of sealants, adhesives, thermal break, cleaning etc. Please consult AkzoNobel.

Contact, even for a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on this coating.

Test conditions

Actual product performance will depend upon the circumstances under which the product is used.

Testing has been determined under laboratory conditions using the following application properties and is for guidance only.

Pre-treatment	Zinc Phosphate
Substrate	Polished steel
Curing schedule	25 min at 160°C
Film Thickness	60 - 80µm

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V5, 25.05.2024

Region: EMEA

AkzoNobel

Technical Datasheet

Interpon 610 Low-E

Low cure polyester powder coating for outdoor use



Mechanical tests

	Typical value	Method/standard
Adhesion	Class 0	ISO 2409 (2 mm Crosshatch)
Erichsen cupping	Pass 5 mm	ISO 1520
Flexibility	Pass 5 mm	ISO 1519
Hardness	Pass - no penetration to substrate	ISO 1518-1 (2000g)
Impact resistance	Pass 2,5 Joules reverse & direct (20 in lb)	ISO 6272-2 (d/r)

Chemical and durability tests

Whilst maintaining the general protective and anti-corrosive properties of powder coatings, aluminum and copper/bronze metallic finishes, when submitted to the listed tests, may rapidly show a loss of metallic aspect. The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.

	Typical value	Method/standard
Chemical Resistance	Generally good resistance to acid, alkalis and oil at room temperatures.	
Salt spray test	Pass, no corrosion creep more than 3 mm from scribe, 500 h	ISO 9227

Environmental and durability tests

	Typical value	Method/standard
Humidity	Pass - no blistering or loss of gloss, 1000 h	ISO 6270-2 CH (Constant humidity)
Exterior durability	Suitable for outdoor use	

Maintenance

For specific advice on Cleaning and Maintenance, please follow Powder Coatings: Cleaning & Maintenance of Surfaces for Industrial use available from AkzoNobel.

Repair

Surface preparation	Damaged areas must be clean and free of grease or rust. Dry-sand the area with 600 grade paper down to the substrate. The area must be completely free of dust and cleaned with a non-aggressive solvent before proceeding. Any damage of the coating system must be repaired as soon as possible.
Application	For repairs a PU (2K or 1K) liquid paint is recommended.

Additional Information

*not applicable for coarse texture finish

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V5, 25.05.2024

Region: EMEA

AkzoNobel

Technical Datasheet

Interpon 610 Low-E

Low cure polyester powder coating for outdoor use



Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.

Disclaimer


IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Appendix

Curing window Interpon 610 Low-E



Disclaimer:

The data contained in this Curing Window graph is obtained from laboratory coating trials under ideal curing conditions, and using perfectly prepared uncoated testing panels; consequently the curing window needs to be regarded as indicative only.

To ensure the correct curing is achieved, specific thermal and performance checks should be

- Minimum cure
- Maximum cure

<http://www.interpon.com/contact-us/>

Copyright © 2024 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel

Revision Date: V5, 25.05.2024

Region: EMEA

AkzoNobel